

# 3D PRINTING N-PLA

Easy to print. Environmentally friendly and non-toxic.  
Perfect for rapid prototyping.  
The material has a very low shrinkage and therefore, there is no deformation.

## PRINTING CHARACTERISTICS

Extrusion temperature	<b>180°C - 230°C</b>
Bed temperature	<b>20°C - 60°C</b>
Enclosure temperature	<b>20°C</b>

Ease of printing




Large size



Machining compatibility



Laser compatibility



 Environmentally friendly



We recommend storing your spools in a dry, dark place, if possible with desiccant. To ensure perfect printing, we recommend steaming your filament at 60°C for 4 hours or more, when the spool has been exposed to the open air for a long period.

Delivered with batch number and material traceability. Coils packed in individual boxes, vacuum-packed with desiccant.

\*According to ISO 527.